PRODUCT SPECIFICATION SHEET



BL DEFORMED BAR - CUT & BEND

NOMINAL SIZE (MM)	WIRE TYPE	CROSS-SECTION AREA (MM²)	MASS PER METER RUN (KG/M)	YIELD STRENGTH RE (N/MM²)	RATIO RM/RE (N/MM²)	AGT (%)
10	DEFORMED	78.5	0.617	500 MIN	1.08 MIN	5.0 MIN
12		113	0.888			
16		201	1.58			
20		314	2.47			
25		491	3.85			
32		804	6.31			
40		1257	9.86			

Note:

- 1. Mass per meter run subjects to the tolerance of \pm /- 4.5% of their nominal values respectively.
- 2. Length is available at 12m maximum and subject to the tolerance of +/-25mm as stated.
- 3. Length in between 2 bends subject to the tolerance of +/-10mm as stated.
- 4 .YBL Deformed Bar Cut & Bend is produced to M\$146:2014 Grade B500B.
- 5 .Source of material is certified to MS146:2014 Grade B500B.











